


Application No. 09/762,765  
 Amdt. dated 12-21-04  
 Reply to Office Action of 09-22-04

2

### Amendments to the Claims:


1. (Cancelled)

2. (Currently amended) The process ~~copolymer~~ of claim 21 ~~claim 4~~ wherein said silicone polymer is a polysilane of the Formula I:



wherein X is an organic end group, W is an organic or inorganic group, with X and W being selected such that the polysilane contains at least two Si-H groups and sufficient to provide a branched structure, and  $n_1$  and  $n_2$  are the number of repeating groups in the chain.


3. (Currently amended) The process ~~copolymer~~ of claim 2 wherein said polysilane of formula I is a polyhydrosiloxane of the formula:



Application No. 09/762,765  
 Amdt. dated 12-21-04  
 Reply to Office Action of 09-22-04

3

4. (Currently amended) The process copolymer of claim 21 ~~claim 4~~ wherein said silicone polymer is a polysilane of the Formula II:




wherein X is an organic end group, W is an organic or inorganic group, with X and W being selected such that the polysilane contains at least two Si-H groups and sufficient to provide a branched structure, and  $n_1$ ,  $n_2$  and  $n_3$  are the number of repeating groups in the chain.


5. (Currently amended) The process copolymer of claim 4 wherein said polysilane of Formula II is a branched polyhydrosiloxane of the formula:

Application No. 09/762,765  
 Amdt. dated 12-21-04  
 Reply to Office Action of 09-22-04

4



6. (Currently amended) The process copolymer of claim 21 ~~claim 4~~, wherein said silane polymer is a polysilane of the formula III:



- III

wherein W is an organic or inorganic group selected such that the polysilane contains at least two Si-H groups and sufficient to provide a branched structure, and n is the number of repeating groups in the chain.



Application No. 09/762,785  
Amdt. dated 12-21-04  
Reply to Office Action of 09-22-04

6

polymer contains free Si-H groups and claim 9 wherein the free Si-H groups are cross-linked.

13. (Previously amended) The copolymer of claim 12 wherein free Si-H groups are converted into a Si-OH group by a metal-catalyzed reaction with water and subsequently dehydrogenatively coupling to a second Si-H group.

14. (Original) The copolymer of claim 12 wherein Si-H groups are reacted by dehydrogenative coupling.

15. (Currently amended) A branched [[The]] copolymer of polypropylene (PP) and a methylhydrosiloxane-dimethylsiloxane random copolymer (MDMS) produced by melt phase hydrosilylation, ~~claim 8~~ which is coupled to metallic, glass, ceramic or other vitreous surface.

16. (Cancelled)

17. (Cancelled)

18. (Original) A process of forming a branched polypropylene, which comprises effecting melt phase hydrosilylation of a terminally-unsaturated polypropylene in the presence of a methylhydrosiloxane-dimethylsiloxane random copolymer (MDMS).

19. (Original) A process of forming a branched polypropylene, which comprises:  
effecting hydrosilylation at a vinyl end of polypropylene with a trialkoxysilane to form a functionalized polymer, and  
thereafter effecting post-reaction branching of the functionalized polymer by reacting Si-OR groups to form a Si-O-Si bridge.

20. (Cancelled)

Application No. 09/762,765  
Amdt. dated 12-21-04  
Reply to Office Action of 09-22-04

7

21. (Previously added) A process of forming a branched copolymer, which comprises:

treating a polyolefin with peroxide to provide terminal unsaturation,  
and  
reacting the terminally-unsaturated polyolefin with a silicone polymer containing at least two Si-H groups in a melt phase reactive extrusion hydrosilylation reaction.

22. (Previously added) The process of claim 21 wherein said polyolefin is polypropylene.

23. (New) The process of claim 18 wherein the ratio of polypropylene to methylhydrosiloxane-dimethylsiloxane random copolymer is such that the polymer contains free Si-H groups.

24. (New) The process of claim 23 wherein said copolymer is coupled, through free Si-H groups, to an inorganic filter, inorganic surface, a hydroxyl-containing polymer, vinyl-containing polymer or other polymer containing functional groups reactive with free Si-H.

25. (New) The process of claims 24 wherein said coupling is effected by a hydrosilylation reaction or a dehydrogenerative coupling reaction.

26. (New) The process of claim 23 wherein the free Si-H groups are cross-linked.

27. (New) The process of claim 26 wherein free Si-H groups are converted into a Si-OH group by a metal-catalyzed reaction with water and subsequently dehydrogenatively coupling to a second Si-H group.

28. (New) The process of claim 26 wherein Si-H groups are reacted by dehydrogenative coupling.

Application No. 09/762,765  
Amdt. dated 12-21-04  
Reply to Office Action of 09-22-04

8

29. (New) The process of claim 18 wherein said copolymer is coupled to metallic, glass, ceramic or other vitreous surface.